Recommendations for the Characterization of RAP Aggregate Properties Using Traditional Testing and Mixture Volumetrics

Elie Y. Hajj*, Peter E. Sebaaly*, Randy West**, Nathan Morian***, and Luis Loria****

*Pavements/Materials Program, Dept of Civil & Env. Engineering, University of Nevada, Reno, NV 89557 elieh@unr.edu psebaaly@unr.edu

** National Center for Asphalt Technology, Auburn University, Auburn, AL, 36849 westran@auburn.edu

*** Nevada Department of Transportation, Carson City, NV 89712 nmorian@dot.state.nv.us

****Laboratorio Nacional de Materiales, Universidad de Costa Rica, Lanamme UCR, San José, Costa Rica luis.loriasalazar@ucr.ac.cr

ABSTRACT. A Federal Highway Administration (FHWA) funded study was conducted to investigate the influence of extraction methods on aggregate properties. The properties of the virgin aggregates were compared to those of aggregates extracted from laboratory-produced recycled asphalt pavement (RAP) with four different aggregate sources. The extracted and actual asphalt binder contents were also compared. The study investigated the influence of the extraction method on tendencies to under or over-estimate certain mix design properties. The test results were also examined to determine the impact of the RAP aggregate properties on the voids in mineral aggregate (VMA) over different RAP percentages. Recommendations were made for the most appropriate method to estimate the RAP aggregate specific gravities based on acceptable levels of error in VMA for mixtures with varying levels of RAP.

KEYWORDS: extraction, centrifuge, ignition oven, reflux, aggregate, VMA

The oral presentation was made by Dr. Hajj.

This is a reproduction of an article whose final and definitive form has been published in *Road Materials and Pavement Design*© 2012 Taylor & Trancis. The article is available online at: http://www.tandfonline.com/doi/abs/10.1080/14680629.2012.657072

1. INTRODUCTION

As reclaimed asphalt pavement (RAP) usage becomes more common throughout the industry, the differences in handling RAP materials as compared to virgin aggregates are becoming more significant. These differences include RAP aggregate properties, such as specific gravity, absorption, and aggregate gradation, along with other properties of the virgin and RAP aggregate blends. Currently, there are no consistent recommendations for assessing the RAP aggregate properties.

Solvent extraction (AASHTO T 164) and the ignition oven method (AASHTO T 308) are currently being used to recover RAP aggregates (AASHTO, 2009) for specific gravity testing and to determine other properties of the aggregate blend such as gradation and Superpave consensus properties. However, there are limitations with both of these methods. The solvent extraction method may leave a residue on the aggregate while the ignition oven method may cause aggregate degradation. Researchers have evaluated the properties of aggregates extracted using the ignition oven method and found that the specific gravities of some aggregates were significantly affected by the ignition oven (Prowell and Carter, 2000). Others also found that aggregate degradation in the ignition oven can be an issue and concluded that the difference in aggregate properties could affect the VMA (Lynn et al., 2007). Evaluations of multiple solvent extraction methods revealed that the asphalt content tended to vary, which may be an indication that some methods were not completely removing the asphalt binder from the aggregate (Shultz, 1998).

2. OBJECTIVE

The objective of this study was to investigate three common extraction methods and their influence on the measured properties of RAP materials including binder content, gradation, and specific gravity of the RAP aggregate and how they influence the VMA calculations in typical hot mix asphalt (HMA) mix designs.

3. RESEARCH APPROACH

The investigation included four aggregate sources: two limestones (hard and soft), a rhyolite, and a granodiorite. The hard limestone was from Calera, Alabama, and the soft limestone was from Brooksville, Florida. The rhyolite was from Reno. Nevada, and the granodiorite was from Gonzales, California. Superpave mix designs were developed for each aggregate source in accordance with AASHTO M 323 (AASHTO, 2009). The mix designs were developed with the virgin aggregates and unmodified asphalt binders. The asphalt binder used for both Alabama and Florida mixes was a PG 67-22 supplied by Ergon, Inc. The asphalt binder used for the Nevada and California mixes was a PG 64-22 supplied by Paramount Petroleum.

The experimental p blends and contrastin aggregates obtained by ignition oven methods. will include the measure both the coarse and fir mixtures containing RA properties, are reported a

The simulated RAF laboratory at the optimu mixing procedures as ou Institute 2001). The mixhours at 135°C) follows condition. To aid in the once per hour during the aging.

After the long-term extraction procedures: ce (i.e. reflux and centrifug solvent. The centrifuge e 164, Method A, while t AASHTO T 164, Metho conducted following AA. completed, the extracted their respective procedure.

4. MIX DESIGN SUMY

All mixtures were demethod (AASHTO M 3 equivalent single axle 1c sources and 3 to 10 milli considered typical traffic the mix design data.

The experimental plan included determining properties of the virgin aggregate blends and contrasting those properties with the laboratory-produced RAP aggregates obtained by extracting the aggregate through the centrifuge, reflux, and ignition oven methods. For the purposes of this paper the reported test properties will include the measured binder content, aggregate gradation and specific gravity of both the coarse and fine aggregates, which all influence the calculated VMA of mixtures containing RAP. The complete data set, including the Superpave consensus properties, are reported elsewhere (Hajj et al., forthcoming).

The simulated RAP materials were prepared by mixing the samples in the laboratory at the optimum binder content for three to five minutes following typical mixing procedures as outlined in the Superpave Mix Design Manual (SP-2) (Asphalt Institute 2001). The mixtures were then subjected to short-term oven aging (four hours at 135°C) followed by long-term oven aging (five days at 85°C), in loose condition. To aid in the uniformity of the binder aging, the mixtures were stirred once per hour during the short-term aging and twice per day during the long-term aging.

After the long-term aging, the mixtures were extracted utilizing the three extraction procedures: centrifuge, reflux, and ignition oven. The solvent extractions (i.e. reflux and centrifuge) were all conducted using trichloroethylene (TCE) as the solvent. The centrifuge extractions were conducted in accordance with AASHTO T 164, Method A, while the reflux extractions were conducted in accordance with AASHTO T 164, Method B (AASHTO, 2009). The ignition oven extractions were conducted following AASHTO T 308 (AASHTO, 2009). Once the extractions were completed, the extracted RAP aggregates were dried and tested in accordance with their respective procedures.

4. MIX DESIGN SUMMARY

All mixtures were designed following the Superpave volumetric mix design method (AASHTO M 323 and R 35 (AASHTO 2009)) for 0.3 to 3 million equivalent single axle loads (ESALs) for the Alabama and California aggregate sources and 3 to 10 million ESALs for the Florida and Nevada sources, which are considered typical traffic levels for those mixtures. Table 1 provides a summary of the mix design data.

nmon throughout npared to virgin le RAP aggregate ation, along with thy, there are no rties.

nod (AASHTO T HTO, 2009) for egate blend such a are limitations ave a residue on ate degradation, sing the ignition iggregates were 00). Others also and concluded onn et al., 2007). asphalt content not completely

raction methods acluding binder and how they x designs.

ones (hard and tlera, Alabama, vas from Reno, ye mix designs SHTO M 323 aggregates and na and Florida r used for the Petroleum.

Table 1. Mix design summary.

Property	Alabama	Florida	Nevada	California
Nominal Max. Aggregate Size (inch)	0.75	0.50	0.75	0.50
PG Binder	67-22	67-22	64-22	64-22
Design ESALs (millions)	2.5	6	6	2.5
Optimum Binder (% TWM)	5.30	6.00	5.85	4.89
Maximum theoretical gravity, G _{mm}	2.537	2.435	2.424	2.422

5. EXTRACTED ASPHALT BINDER CONTENTS

Figure 1 and Table 2 illustrate the asphalt binder contents obtained from each extraction method along with their 95% confidence intervals. The properties of the extracted RAP aggregates were compared to the properties of the virgin aggregates using statistical analyses at a significance level of 0.05. The following nomenclatures were used in all the paired mean comparison statistical analysis tables:

- NS the measured property for the extracted aggregates is not significantly different from the virgin aggregates;
- SL the measured property for the extracted aggregates is significantly lower than the virgin aggregates;
- SH the measured property for the extracted aggregates is significantly higher than the measured property of the virgin aggregates.

Overlapping of the confidence intervals indicates similarities in the extracted binder contents from the various extraction methods. Note that no correction factors were used for the ignition oven results as they are not expected to be available for actual RAP materials from the field. The true asphalt binder contents were assumed to be the designed asphalt binder content for each mix as they were mixed.

Examination of the results indicates that the true asphalt binder contents were consistently higher than the asphalt binder contents obtained from all of the extraction methods. The centrifuge method yielded the lowest asphalt binder content for all four aggregate sources while the ignition oven yielded the highest asphalt binder content.

The asphalt binder contents of each mix for a given extraction method were statistically compared to the corresponding true asphalt binder content using the student t-test at a 0.05 significance level. Table 2 summarizes the results of the t-tests conducted. In almost all cases, the null hypothesis was rejected, indicating that all the extracted asphalt binder contents were significantly lower than the true asphalt binder contents except for the Nevada and California aggregates using the reflux method.

True Binder

☐ Centrifuge ☐ Reflux

☑ Ignition Over

Figure 1. Bis

Table 2. Ex.

	Extraction Method	Aggra Sou		
		Alaba		
	0	Florid		
1	Centrifuge	Neva		
		Califo		
		Alaba		
	D - 6	Florid		
	Reflux	Neva		
		Califo		
		Alaba		
1	Ignition	Floriô		
1	Oven	Nevar		

*Confi *signifies the measu

Califo

6.5 6.0 5.5 5.0 4.5 4.0 Alabama California Nevada Florida (Soft (Hard (Granodiorite) (Rhyolite) Limestone) Limestone) 5.85 4.89 5.30 6.00 ■ True Binder Content 4.61 5.65 □ Centrifuge 4.87 5.43 5.76 4.70 4.98 5.62 □ Reflux 5.79 4.82 ☑ Ignition Oven 5.13 5.80

Figure 1. Binder contents (whiskers represent 95% confidence interval).

Table 2. Extracted asphalt binder contents and t-test results (% TWM).

Extraction Method	Aggregate Source	Rep	Difference Between Extracted and True Binder Contents	Allowable Difference (d2s)	p-value α=0.05	95% CIª	Sig. level ^b
	Alabama	13	0.430		< 0.001	4.70-5.04	SL
	Florida	12	0.570°	0.520	< 0.001	5.29-5.57	SL
Centrifuge	Nevada	4	0.200	0.320	< 0.001	5.62-5.68	SL
	California	4	0.280		0.002	4.53-4.69	SL
	Alabama	15	0.320		< 0.001	4.85-5.11	SL
	Florida	12	0.380	0.520	< 0.001	5.51-5.73	SL
Reflux	Nevada	4	0.090	0.520	0.082	5.65-5.87	NS
	California	4	0.190		0.154	4.38-5.02	NS
	Alabama	14	0.170		0.024	4.99-5.27	SL
Ignition	Florida	14	0.200°	0.106	0.001	5.70-5.90	SL
Oven	Nevada	3	0.060	0.196	0.001	5.77-5.81	SL
	California	3	0.070		0.007	4.80-4.85	SL

^aConfidence Interval ^b SL: significantly lower, NS: not significant ^csignifies the measurement is not within the d2s tolerance as compared to the virgin material.

0.50 0.4-22 2.5 4.89 2.422

Asphalt Content, (%)

from each fies of the aggregates following analysis

gnificantly

gnificantly

gnificantly

extracted ion factors ailable for e assumed

tents were all of the ier content est asphalt

thod were using the ts of the tcating that n the true s using the

Further investigation into the differences of the determined binder contents were considered based upon the precision and bias statements of the respective test methods. The precision statements of the three extraction test methods utilize the d2s parameter as the allowable difference between two replicates of the same sample tested by the same person on the same equipment, which is a significantly smaller allowable margin of error than if the tolerance were corrected for the actual number of replicates following ASTM C670-03. Table 2 indicates that nearly all of the measured binder contents are within the d2s tolerance for their respective extraction procedures. The only exceptions are the centrifuge results from Florida, which are barely out of the tolerance for the centrifuge and ignition oven. Given that the Florida centrifuge results were based upon 12 replicates and the ignition oven results were based upon 14 replicates rather than two, it can be stated that the tested binder contents are generally within the d2s tolerance for all mixes and extraction methods.

Once the extractions were completed, the extracted aggregates were dried and tested in accordance with their respective procedures as if the material had been virgin aggregate. In all cases, three replicates were used to measure the aggregate properties with all the test results falling within the permissible difference between three results (d3s) for single operator precision considerations.

6. SIEVE ANALYSIS

The sieve analyses of the virgin and extracted aggregates were conducted in accordance with AASHTO T 27 (AASHTO, 2009). Table 3 shows the gradations for the virgin and extracted RAP aggregates at selected sieve sizes.

In order to distinguish any significant differences in the test results, a one-way (i.e., single factor) analysis of variance (ANOVA) with an alpha level of 0.05 was conducted for each of the aggregate sources to determine if the extraction processes contributed to the variability. Paired mean comparisons were also conducted to determine if there were differences between the means of percent passing a given sieve of the virgin aggregates and extracted aggregates as shown in Table 3. The acceptable range of two results, d2s, is presented for each source as well. These values are included to further help differentiate the dissimilarities in the measured properties. If for instance, two results are significantly different, but both are within the allowable tolerance, d2s, then the two results should not be considered significantly different from a practical standpoint. The acceptable ranges vary by the respective sources since the d2s parameters are scaled by the percent passing each particular sieve being considered.

Table 3. Extra



Table 3. Extracted RAP aggregate gradation and paired mean comparison results.

Source	Extraction			Si	eve Size (mm)	
	Method	Property	12.5	4.75	2.36	0.300	0.0
	None	% passing	93.2	52.1	38.4	11.1	5.4
	0 10	% passing	93.4	51.9	37.8	11.0	5.4
r	Centrifuge	Difference	+0.2	-0.2	-0.6	-0.1	+0.
		Significance	NS	NS	NS	NS	NS.
41-1		% passing	91.8	50.0	36.6	10.7	5.5
Alabama	Reflux	Difference	-1.4	-2.1	-1.8	-0.4	+0.
		Significance	NS	SL	SL	NS	NS
	Ignition	% passing	92.6	50.8	37.3	12.4	7.60
	Oven	Difference	-0.6	-1.3	-1.1	+1.3	+2.2
	100-100-100	Significance	NS	NS	NS	SH	SH
		table d2s	2.3	3.7	3.7	2.8	2.1
	None	% passing	100	54.7	36.9	9.3	5.63
		% passing	100	50.1	33	6.3	2.4
	Centrifuge	Difference	+0.0	-4.6	-3.9	-3.0	+3.2
		Significance	NS	NSd	SL ^d	SL	SL ^d
		% passing	100	52.6	34.5	7.3	
Florida	Reflux	Difference	+0.0	-2.1	-2.4	-2.0	2.81 -2.8
		Significance	NS	NS	SL	SL SL	-2.8 SL ^d
	Imitian	% passing	100	51.8	33.6	6.9	
Ignition Oven		Difference	+0.0	-2.9	-3.3	-2.4	2.56
	Oven	Significance	NS	NS	NS	NS ^d	-3.1
	Accept	able d2s	0.9	3.7	3.7		SLd
	None	% passing	94.2	58.8	43.1	2,1	1.5
		% passing	94.6	59	42.9	16.3	5.9
	Centrifuge	Difference	+0.4	+0.2		18.1	5.78
		Significance	NS	NS NS	-0.2 NS	+1.8	-0.1
		% passing	94.1	59.5		SH	NS
Nevada	Reflux	Difference	-0.1	+0.7	42.5	16.8	6.02
		Significance	NS	NS NS	-0.6	+0.5	+0.1
		% passing	94.3		NS	NS	NS
l l	Ignition	Difference	+0.1	57.9	41.8	16.3	4.68
	Oven	Significance	NS	-0.9	-1.3	+0.0	-1.2
	Accepta		2.3	NS	SL	NS	SL
	None	% passing	86.1	3.7	3.7	2.7	1.5
	Trone	% passing		40.7	23.5	9.9	4.3
	Centrifuge	Difference	86.5	40.9	24.9	11.6	5.4
		Significance	+0.4	+0.2	+1.4	+1.7	+1.1
ł		% passing	NS	NS	SH	SH	SH
California	Reflux		86.3	42.2	25.7	12.2	6.23
- Little		Difference	+0.2	+1.5	+2.2	+2.3	+1.9
ł		Significance	NS	SH	SH	SH	SH
	IPHIHOD	% passing	86.3	42.2	25.7	12.2	6.23
	Oven	Difference	+0.6	+1.6	+2.1	+2.2	+1.7
1		Significance	NS	SH	SH	SH	SH
	Acceptat gnifies the meas	oie d2s	2.3	3.7	3.7	2.8	2.1

ried and i been gregate between

n methods.

nducted in idations for

a one-way f 0.05 was processes aducted to ng a given ble 3. The rell. These measured are within considered rary by the ssing each

Based on the results shown in Table 3, the following observations can be made:

- The extracted RAP aggregates using the centrifuge method did not have consistently lower or higher percent passing a specific sieve size when compared to virgin aggregates. The centrifuge method did not have a significant impact on the extracted aggregate gradation from the Alabama and Nevada RAP mixes, but did have a statistically significant impact on the fine portion (i.e., < 2.36 mm sieve) of the extracted aggregates from the Florida and California RAP mixes.
- The extracted RAP aggregates using the reflux method did not have consistently lower or higher percent passing a specific sieve size when compared to virgin aggregates. Except for the Nevada RAP mix, the reflux method generally had a statistically significant impact on the percent passing sieve sizes finer than the 4.75 mm sieve.
- The extracted RAP aggregates using the ignition oven method generally created either significantly higher or significantly lower percent passing the sieve sizes smaller than 4.75 mm, with minor influences on sieve sizes greater than 4.75 mm when compared to virgin aggregates.
- With respect to the acceptable difference between two test results, the majority of the differences fell within the allowable range. Only the ignition oven passing the 0.075 mm sieve from Alabama and several of the Florida gradations did not meet the d2s requirements. Most of the Florida centrifuge sieves, except the 4.75 mm, were outside the permissible limits as were the 0.300 and 0.075 mm for the ignition and the 0.075 mm for the reflux methods.

7. COARSE AND FINE AGGREGATE BULK DRY SPECIFIC GRAVITIES

The specific gravities of the virgin and extracted coarse and fine aggregates were measured in accordance with AASHTO T 85 and T 84, respectively (AASHTO, 2009). Table 4 summarizes the data for the measured bulk specific gravities and provides the results of the mean comparison analysis that was conducted to determine if the specific gravities of the various extracted aggregates were significantly different from those of the virgin aggregates.

From the data in Table 4 the following observations can be made for the coarse aggregate specific gravities:

 The extracted coarse aggregates using the centrifuge method did not consistently have lower or higher bulk dry specific gravity when compared with the virgin aggregates.

- The spe vir:
- The spe for ign vir
- AA sing diff agg pro

Similarly gravities:

- The are spe
- The sign exc gra
- The or h virg
- AA sing diff agg pro and

- The extracted coarse aggregates using the reflux method had bulk dry specific gravities that are either similar to or significantly higher than the virgin aggregates specific gravities.
- The extracted coarse aggregates using the ignition oven had bulk dry
 specific gravities that were significantly lower than the virgin aggregates
 for three out of four aggregate sources. The bulk specific gravity of the
 ignition oven extracted California aggregate was statistically similar to the
 virgin aggregate specific gravity.
- AASHTO T 85 states that the allowable difference between two results by a single operator between true replicates should not exceed 0.025. While the differences between the specific gravities of the virgin and extracted coarse aggregates are not a comparison of true replicates, those differences can provide a good indication of the relative closeness of the obtained results.

Similarly, the following observations can be made for the fine aggregate specific gravities:

- The centrifuge extracted fine aggregates had bulk dry specific gravities that are either similar to or significantly higher than the virgin aggregates specific gravities.
- The reflux extracted fine aggregates had bulk dry specific gravities that are significantly higher than the virgin aggregates specific gravities with the exception of the aggregates from Nevada, which had similar specific gravities.
- The ignition oven extracted fine aggregates did not have consistently lower or higher fine aggregate bulk dry specific gravities when compared to the virgin materials.
- AASHTO T 84 states that the allowable difference between two results by a single operator between true replicates should not exceed 0.032. While the differences between the specific gravities of the virgin and extracted fine aggregates are not a comparison of true replicates, those differences can provide a good indication of the relative closeness of the obtained results and in this case are in close agreement with the statistical comparisons.

made:

not have te when have a Alabama apact on from the

not have ze when he reflux percent

generally ssing the eve sizes

sults, the e ignition the Florida florida ble limits m for the

VITIES

rates were AASHTO, vities and ducted to ates were

the coarse

d did not compared

Table 4. Coarse and fine aggregate dry bulk specific gravities.

Extraction Method	Agg. Source	Ave.	STD	Max Difference (Max- Min)	Difference Between Extracted and Virgin Aggregates	Allowable Difference Two Sigma (d2s)	Paired Mean Comp.
			Coars	e Aggregates			
	Alabama	2.739	0.007	0.013			
	Florida	2.419	0.009	0.017	-		
None	Nevada	2.584	0.008	0.018	-		
	California	2.544	0.004	0.008	_		-
	Alabama	2.728	0.008	0.015	-0.011		NS
	Florida	2.430	0.005	0.009	0.011		SH
Centrifuge	Nevada	2.569	0.003	0.005	-0.015	0.025	SL
	California	2.521	0.007	0.014	-0.023		SL
	Alabama	2.725	0.002	0.003	-0.014		NS
2.2	Florida	2.429	0.006	0.010	0.010		SH
Reflux	Nevada	2.581	0.004	0.008	-0.003	0.025	NS
	California	2.561	0.003	0.006	0.017		SH
	Alabama	2.683	0.004	0.007	-0.056°		SL
Ignition	Florida	2.400	0.007	0.013	-0.019	0.025	SL
Oven	Nevada	2.564	0.007	0.015	-0.020		SL
	California	2.538	0.006	0.012	-0.006		NS
		2.000		Aggregates	0.000		
	Alabama	2.661	0.004	0.007			
	Florida	2.585	0.010	0.010			
None	Nevada	2.491	0.010	0.019		-	
	California	2.541	0.009	0.017			
	Alabama	2.711	0.015	0.029	0.050		SH
NEW TOTAL BARRIES	Florida	2.583	<0.001	0.010	-0.002	N	NS
Centrifuge	Nevada	2.486	0.016	0.031	-0.005	0.032	NS
	California	2.577	0.010	0.021	0.036*		SH
	Alabama	2.718	0.010	0.019	0.057		SH
52 27	Florida	2.622	0.010	0.020	0.037 *		SH
Reflux	Nevada	2.522	0.013	0.025	0.031	0.032	NS
	California	2.576	0.010	0.021	0.035		SH
	Alabama	2.690	0.004	0.007	0.029		SH
Ignition	Florida	2.521	0.010	0.020	-0.064*		SL
Oven	Nevada	2.512	0.017	0.032	0.021	0.032	NS
	California	2.583	0.008	0.015	0.042		SH

signifies the measurement is not within the d2s tolerance when compared to the virgin material.

8. COMBINED AGGREGATE SPECIFIC GRAVITY

The combined dry bulk specific gravities for the virgin and extracted aggregates of each aggregate source were calculated according to Equation 1 using the average values for the measured corresponding coarse and fine bulk dry specific gravities.

where,

Tab
aggrega
aggrega
for the
aggrega
calculat
the virg
aggrega
Alabam
aggrega

 $G_{sb} = \frac{\sum_{i=1}^{n} P_i}{\sum_{i=1}^{n} G_i}$ [1]

where,

 G_{sb} = combined aggregate bulk dry specific gravity P_i = percentage of aggregate fraction i

 G_i = aggregate dry bulk specific gravity of fraction i n = number of aggregate fractions

Table 5 shows the data for the combined dry bulk specific gravity for the various aggregate sources. The calculated combined G_{sb} of the centrifuge extracted aggregates was slightly lower than the virgin aggregate combined specific gravity for the Florida and Nevada aggregates and higher for the Alabama and California aggregates. On the other hand, the reflux method resulted consistently in a calculated combined G_{sb} value that is higher than the combined specific gravity of the virgin aggregates. The calculated combined G_{sb} of the ignition oven extracted aggregates was lower than the virgin aggregate combined specific gravity for the Alabama and Florida aggregates and higher for the Nevada and California aggregates.

ravities.

llowable ifference Two Sigma (d2s)	Paired Mean Comp.
	-
	NS
0.025	SH
0.025	SL
	SL
	NS
0.025	SH
0.025	NS
	SH
	SL
0.025	SL
0.025	SL
	NS
	-
-	
	-
	SH
0.032	NS
0.032	NS .
	SH
	SH
0.032	SH
0.032	NS
	SH
	SH
0.032	SL
0.052	NS
	SH

irgin material.

tracted aggregates using the average ecific gravities.

Table 5. Properties of virgin and extracted aggregates.

							_						_			
Mix bulk gravity, 4% voids, Gmb	2.44				7 33	67			233	66.77						
Abs. asphalt, P_{ba}	0.89	0.32	0.36	0.93	2.41	2.09	1.85	3.02	1.90	1.92	1.58	1.78	1.01	0.82	0.51	0.75
Eff. specific gravity, G _{se}	2.764	2.743	2.748	2.756	2.668	2.643	2.651	2.659	2.656	2.647	2.652	2.654	2.610	2.598	2.602	2.607
Percent asphalt TWM, P_b	5.30	4.87	4.98	5.13	00.9	5.43	5.62	5.80	5.85	5.65	5.76	5.79	4.89	4.61	4.70	4.82
Max. Theor.,		7537	755.7			2010	6.433			2 431	164.7			7.477	174.7	
Diff.	ŧ	0.021	0.024	-0.011	1	-0.003	0.020	-0.046	1	-0.009	0.017	0.005	1	0.025	0.025	0.014
Comb.	2.698	2.719	2.721	2.687	2.507	2.504	2.527	2.461	2.528	2.519	2.546	2.534	2.543	2.568	2.567	2.557
% Fines	52.1	51.9	50.0	50.8	54.7	50.1	52.6	51.8	58.8	59.0	59.5	57.9	40.7	40.9	42.2	42.3
Fine Gsb	2.661	2.711	2.718	2.690	2.585	2.583	2.622	2.521	2.491	2.486	2.522	2.512	2.541	2.577	2.576	2.583
Coarse Gsb	2.739	2.728	2.725	2.683	2.419	2.430	2.429	2.400	2.584	2.569	2.581	2.564	2.544	2.521	2.561	2.538
Extraction Method	None	Centrifuge	Reflux	Ignition												
Source		Alabama				Florida				Nevada				California		

9. EFFECT O MINERAL AC

The specific volumetric calc of each aggreg calculation of following three of the RAP agg

- Metho fractic 4.75 n would ignitic
- Metho with 1 RAP This 1 RAP 2
- Methors the bulk RAP the R.

The impact RAP aggregate between 10 ar measured aspt the combined specific gravit the calculated specific gravit; source using determined a corresponding (P_{ba}) was deter Equation 3 and

Gan :

P_{ba} =

9. EFFECT OF RAP AGGREGATE PROPERTIES ON VOIDS IN MINERAL AGGREGATE (VMA)

The specific gravity of the combined gradation of aggregates is required for the volumetric calculations of an HMA mix design. Therefore, the bulk specific gravity of each aggregate stockpile, including the RAP, needs to be determined for the calculation of the bulk specific gravity of the combined aggregate blend. The following three methods have been historically used to estimate the specific gravity of the RAP aggregate (G_{sb}) .

- Method A: use the measured specific gravities of the coarse and fine fractions of the extracted RAP aggregate along with the percent passing the 4.75 mm sieve in the RAP to calculate the combined specific gravity. This would require extracting the RAP aggregate using the centrifuge, reflux, or ignition oven method.
- Method B: use an assumed asphalt absorption for the RAP aggregate along
 with the determined theoretical maximum specific gravity (G_{mm}) of the
 RAP mixture to back-calculate the RAP aggregate bulk specific gravity.
 This would require a good estimate of the percent absorbed asphalt in the
 RAP aggregates.
- Method C: use the RAP aggregate effective specific gravity (G_{se}) in lieu of the bulk specific gravity (G_{sb}). This would require the determination of the RAP binder content and the theoretical maximum specific gravity (G_{mm}) of the RAP.

The impact of the errors associated with the different methods of estimating the RAP aggregate G_{sb} on the calculation of VMA was evaluated for RAP percentages between 10 and 50% in a typical asphalt mixture. For each aggregate source, the measured asphalt binder contents and aggregate properties were used to determine the combined aggregate bulk specific gravities (G_{sb}) (Equation 1), the effective specific gravities (G_{sc}) and the percent absorbed asphalt (P_{ba}). Table 5 summarizes the calculated properties for the virgin and extracted aggregates. The effective specific gravity (G_{sc}) was determined for the virgin and extracted aggregates of each source using Equation 2 and the maximum theoretical specific gravity (G_{mm}) determined after long-term oven aging. For each extraction method, the corresponding asphalt binder content (P_{b}) was used. The percent of absorbed asphalt (P_{ba}) was determined for the virgin and extracted aggregates from each source using Equation 3 and the corresponding combined G_{sb} and G_{sc} .

$$G_{se} = \frac{100 - P_b}{\frac{100 \quad P_b}{G_{mm} \quad G_b}}$$
 [2]

$$P_{ba} = 100 \left(\frac{G_{se} - G_{sb}}{G_{se} G_{sb}} \right)$$
 [3]

where.

 P_b = percentage of asphalt by total weight of mix G_b = asphalt binder specific gravity G_{mm} = maximum theoretical specific gravity

9.1. Impact of Method A on the Calculation of VMA

Method A requires the use of the combined aggregate specific gravity (G_{sb}) that was calculated using the measured corresponding specific gravities for the coarse and fine fractions of the extracted RAP aggregate along with the percent fine material (i.e., passing the 4.75 mm sieve) in the RAP. The blend aggregate specific gravity is calculated using the virgin aggregate specific gravity and the RAP aggregate specific gravity for different RAP percentages. Additionally, the calculated blend G_{sb} was compared to the G_{sb} of the virgin aggregates (i.e., 0% RAP) and the difference was calculated for RAP percentages between 0 and 50% (Figure 2). Further, VMA is calculated by Equation 4 for different RAP percentages using the blend G_{sb} and the mixture bulk specific gravity (G_{mb}) and percent asphalt binder (P_{b}). In this study, the properties of the asphalt mixtures (i.e., G_{mb} , P_{b} , G_{mm}) before extraction were used to calculate the VMA.

$$VMA = 100 - \frac{G_{mb} \times (100 - P_b)}{G_{sb}}$$
 [4]

Additionally, the calculated VMA was compared to the VMA of the virgin mix (i.e., 0% RAP) and the difference was considered for RAP percentages up to 50%. Figures 2 through 4 show the differences in blend G_{sb} and VMA for all four aggregate sources at 10, 30 and 50% RAP.

The errors for the calculated blend G_{sb} tended to vary. The impact of the extraction method on the blend G_{sb} can be summarized as follows.

- The centrifuge resulted in an error in the blend G_{sb} of between 0.000 and -0.005, with the exception of the Alabama hard limestone aggregate where the error varied from a value of 0.002 at 10% RAP to a maximum of 0.011 at 50% RAP.
- The reflux consistently overestimated the blend G_{sb}. The error varied from a value of 0.002 at 10% RAP to a maximum between 0.009 and 0.012 at 50% RAP.
- The ignition oven resulted in an error in the blend G_{sb} of maximum between -0.006 and 0.007 at 50% RAP, with the exception of the Florida soft limestone aggregate where the error varied from a value of -0.005 at 10% RAP to a maximum of -0.023 at 50% RAP.

Figure 2.




Figure 2. (a) Difference in blend G_{sb} and (b) VMA for 10% RAP content, Method A.

(b)

ravity (G_{sb}) that for the coarse he percent fine gregate specific and the RAP iditionally, the (i.e., 0% RAP) nd 50% (Figure reentages using a sphalt binder P_b, G_{mm}) before

[4]

f the virgin mix ages up to 50%. 4A for all four

: impact of the

tween 0.000 and stone aggregate P to a maximum

The error varied ween 0.009 and

i_{sb} of maximum on of the Florida alue of -0.005 at




Figure 3. (a) Difference in blend G_{sb} and (b) VMA for 30% RAP content, Method A.

(b)

■ Alabama (hard limestone)

■ Nevada (rhyolite)

Extraction Method

⊟ Florida (soft limestone)

☐ California (Granodiorite)

Figure 4. (a

The imp

- bet har
- Usi val bet




Figure 4. (a) Difference in blend Gst and (b) VMA for 50% RAP content, Method A.

The impact of the extraction method on the VMA can be summarized as follows.

- Using the centrifuge test information resulted in an error in the VMA of between -0.16 and 0.01 at 50% RAP, with the exception of the Alabama hard limestone aggregate where the error varied from a value of 0.07 at 10% RAP to a maximum of 0.34 at 50% RAP.
- Using the reflux results led to the consistent overestimation of the VMA values. The error varied from a value of 0.07 at 10% RAP to a maximum between 0.29 and 0.42 at 50% RAP, for all the sources.

thod A.

 Using the ignition oven test information resulted in a maximum error in the VMA between -0.18 and 0.24 at 50% RAP, with the exception of the Florida soft limestone aggregate where the error varied from -0.16 at 10% RAP to a maximum of -0.82 at 50% RAP.

9.2. Impact of Method B on the Calculation of VMA

Method B represents an alternative approach for estimating the RAP aggregate G_{sb} that was recommended in NCHRP Report 452 (McDaniel and Anderson, 2001) which is based on assuming a value for the asphalt absorption of the RAP aggregate (i.e. P_{ba}). The bulk specific gravity of the RAP aggregate can be calculated based on this assumed absorption using Equation 5. This G_{sb-est} value can then be used to estimate the blend aggregate bulk specific gravity for different RAP percentage and to calculate VMA.

$$G_{Sb-est} = \frac{G_{se}}{\left(\frac{P_{ba}G_{se}}{100 \times G_b}\right) + 1}$$
 [5]

In actual practice, the P_{ba} true value for a given RAP source will be unknown, therefore, mix designers will need to estimate the P_{ba} based on the typical values from asphalt mixes where the RAP was obtained. Therefore, this study evaluated the impact of the $G_{\text{sb-est}}$ on VMA for an assumed asphalt absorption equal to the true P_{ba} value and for $\pm~25\%$ variations in the true P_{ba} value. The true P_{ba} was calculated from the properties of the virgin aggregates (i.e., no extraction). P_{ba} values of 0.89%, 2.41%, 1.90% and 1.01%, were calculated for the virgin aggregates from Alabama, Florida, Nevada, and California, respectively.

The blend aggregate specific gravity is calculated using the virgin aggregate specific gravity and the estimated RAP aggregate specific gravity ($G_{\text{sb-est}}$) for different RAP percentages. The VMA was calculated using Equation 4 and the determined blend G_{sb} for different RAP percentages. Figures 5 to 7 show the differences in blend G_{sb} and VMA for all four aggregate sources at 10, 30, and 50% RAP and for different levels of P_{ba} .




Figure 5. (a) D

in the

of the

it 10%

pregate 2001) pregate sed on used to

ge and

cnown,

values

ted the

rue P_{ba} culated

0.89%,

abama,

gregate

est) for

ind the

ow the

nd 50%

[5]




Figure 5. (a) Difference in blend G_{sb} and (b) VMA for 10% RAP content, Method B.





Figure 6. (a) Difference in blend G_{sb} and (b) VMA for 30% RAP content, Method B.

Figure 7. (

Difference in Blend Gsb



5Pba

Pba

thod B.

Figure 7. (a) Difference in blend G_{sb} and (b) VMA for 50% RAP content, Method B.

The following summarizes the impact of the extraction method on VMA when the assumed asphalt absorption was 25% below the true P_{ba} .

- The centrifuge results led to an error in the VMA between -0.01 and 0.09 at 10% RAP and an error between -0.04 and 0.43 at 50% RAP.
- The reflux results consistently overestimated the VMA values. The error in VMA varied between 0.01 and 0.10 at 10% RAP to a maximum between 0.04 and 0.50 at 50% RAP.
- The ignition oven resulted in consistently overestimated VMA values over the different RAP percentages. The error in VMA varied between 0.03 and 0.12 at 10% RAP to a maximum between 0.15 and 0.52 at 50% RAP.

The following summarizes the impact of the extraction method on VMA when the true asphalt absorption (P_{ba}) is used to estimate the specific gravity (G_{sb-est}) of the RAP aggregates.

- The centrifuge results consistently underestimated the VMA values over the considered range of RAP percentages. The error in VMA varied between -0.02 and -0.07 at 10% RAP to a maximum between -0.08 and -0.32 at 50% RAP.
- Using the reflux test information resulted consistently in an underestimation in the VMA values at different RAP percentages. The error in VMA varied between 0.00 and -0.04 at 10% RAP to a maximum between -0.01 and -0.21 at 50% RAP.
- Using the ignition oven test information resulted in a maximum error in VMA of -0.02 at 10% RAP and an error between -0.10 and 0.02 at 50% RAP.

The following summarizes the impact of the extraction method on VMA when the assumed asphalt absorption was 25% higher than the true P_{ba} .

- The centrifuge results consistently underestimated the VMA at different RAP percentages. The error in VMA varied between -0.09 and -0.19 at 10% RAP to a maximum error between -0.43 and -0.97 at 50% RAP.
- The reflux results consistently underestimated the VMA values at different RAP percentages. The error in VMA varied between -0.07 and -0.17 at 10% RAP to a maximum error between -0.37 and -0.84 at 50% RAP.
- The ignition oven results consistently underestimated the VMA at different RAP percentages. The error in VMA varied between -0.06 and -0.14 at 10% RAP to a maximum error between -0.29 and -0.71 at 50% RAP.

In summary, when the true P_{ba} is used, the ignition oven led to a minimal error in VMA, followed by the reflux and the centrifuge. When the assumed asphalt absorption was 25% lower than the true P_{ba} , all three extraction methods led to

similar erro the assume ignition ov centrifuge v

9.3 Impact

According the past instead of from the report to binder combinder specifrom Equal used to calculate the aggregate of the past of the past

Difference in VMA

similar errors in VMA. A significant increase in the VMA error was observed when the assumed asphalt absorption was 25% higher than the true P_{ba} . Relatively, the ignition oven led to the least error in VMA, followed by the reflux and the centrifuge with 1.25 P_{ba} .

9.3 Impact of Method C on the Calculation of VMA

According to NCHRP Report 452 (McDaniel and Anderson, 2001), some states in the past have used the effective specific gravity (G_{se}) of the RAP aggregate instead of its bulk specific gravity (G_{sb}). The effective specific gravity is calculated from the measured RAP maximum specific gravity (G_{mm}). Typically, the asphalt binder content of the RAP is determined by extraction or ignition oven and the binder specific gravity is assumed, the effective specific gravity is then calculated from Equation 2. This estimate of the RAP aggregate effective specific gravity is used to calculate the combined aggregate specific gravity, which is then used to calculate the VMA. Figures 8 to 10 show the differences in VMA for all four aggregate sources at 10, 30, and 50% RAP.




Figure 8. Difference in VMA for 10% RAP content, Method C.

on VMA when

0.01 and 0.09 at

es. The error in

4A values over tween 0.03 and)% RAP.

on VMA when $f(G_{\text{sb-est}})$ of the

A values over VMA varied en -0.08 and -

ently in an ages. The error a maximum

imum error in i 0.02 at 50%

n VMA when

A at different and -0.19 at a RAP.

es at different and -0.17 at RAP.

A at different and -0.14 at RAP.

imal error in med asphalt thods led to




Figure 9. Difference in VMA for 30% RAP content, Method C.




Figure 10. Difference in VMA for 50% RAP content, Method C.

In all cases, the blend G_{sb} was overestimated with the error increasing with the RAP percentage. This result was expected since the G_{se} value is larger than the corresponding G_{sb} value. The error in G_{sb} was as low as 0.004 at 10% RAP and as high as 0.074 at 505 RAP. The VMA was calculated using Equation 4 and the determined blend G_{sb} for different RAP percentages. The following summarizes the impact of the extraction method on VMA when the effective specific gravity (G_{se}) is used for the RAP instead of the bulk specific gravity (G_{sb}).

10. SUN

10.1. Im

The of the R each of compare virgin a between evaluate RAP.

Tabl sources indicate respecti 12.5 m signific

The extracti content which s was m measur

In to the exextraction the distribu

- The centrifuge results consistently overestimated the VMA values at different RAP percentages. The error in VMA varied between 0.14 and 0.45 at 10% RAP to a maximum between 0.71 and 2.25 at 50% RAP.
- The reflux results consistently overestimated in the VMA values at different RAP percentages. The error in VMA varied between 0.16 and 0.48 at 10% RAP to a maximum between 0.79 and 2.38 at 50% RAP.
- The ignition oven results consistently overestimated the VMA values at different RAP percentages. The error in VMA varied between 0.18 and 0.50 at 10% RAP to a maximum between 0.90 and 2.51 at 50% RAP.

10. SUMMARY OF FINDINGS

10.1. Impact of Extraction Method on RAP Properties

The asphalt binder content of the RAP mix, the gradation, and specific gravities of the RAP aggregate were compared with respect to three extraction methods for each of the four aggregate sources (Hajj et al., forthcoming). Statistical analyses compared the properties of the extracted RAP aggregates with the properties of the virgin aggregates at a significance level of 0.05 as well as the allowable tolerance between two test results, d2s. Furthermore, the final impact of these changes was evaluated in terms of their impact on the calculated VMA of mixtures containing the RAP.

Table 6 summarizes the combined statistical significance for all four aggregate sources grouped by the evaluated extraction methods. The values in the table indicate how many of the four aggregate sources correspond to that result for each respective comparison. For example, a "4" under the centrifuge-NS across from the 12.5 mm sieve means that for all four aggregate sources the centrifuge did not significantly impact the percent passing the 12.5 mm sieve.

The data in Table 6 show that the asphalt binder contents measured by all three extraction methods were statistically significantly lower than the true asphalt binder contents except for the Nevada and California aggregates using the reflux method, which showed binder contents statistically similar to the true levels. This similarity was mainly due to the large amount of variability observed in the reflux measurements with Nevada and California RAP mixes.

In the case of aggregate properties, it is clear from Table 6 that, overall, none of the extraction methods consistently impacted the measured properties of the extracted aggregates. While none of the extraction methods had a significant impact on the size distributions of the coarse portion of the aggregates, the effect on the size distribution of the fine portion of the aggregates was aggregate source-dependent.

Table 6. Comparison of binder content and aggregate properties.

Buomonting	C	entrifi	ıge	Reflux			Ignition Oven		
Properties	SL	NS	SH	SL	NS	SH	SL	NS	SH
Asphalt binder content	4			2	2		4		
Sieve analysis						*****		-	
- 12.5 mm sieve		4			4			4	
- 4.75 mm sieve		4		1	2	1		3	1
- 2.36 mm sieve	1	2	1	2	1	1	1	2	1
- 0.300 mm sieve	1	1	2	1	2	1		2	2
- 0.075 mm sieve	1	2	1	1	2	1	2		2
 Coarse bulk specific gravity, dry 	2	1	1		2	2	3	1	
Fine bulk specific gravity, dry		2	2		1	3	1	1	2

The impact of the extraction method on the bulk specific gravity of coarse and fine aggregates was method-dependent. The impact of the centrifuge on the coarse aggregate specific gravity of the various sources was also inconsistent. However, the centrifuge led to aggregate properties with either similar or significantly higher fine aggregate specific gravities than the virgin aggregate. The reflux consistently produced aggregates with either similar or significantly higher coarse and fine aggregate specific gravities than the virgin aggregate. The ignition oven produced aggregates with either similar or significantly lower coarse aggregate specific gravities than virgin aggregate. However, the impact of the ignition oven on the fine aggregate specific gravities was inconsistent across the different sources.

The impact of the extraction method on the combined aggregate specific gravity is more critical than their impact on the individual specific gravities, since it is the combined specific gravity that is used to calculate the volumetric properties of the mix. The analysis of these data showed that the impact on the combined specific gravity was method-dependent as well:

- Centrifuge: slightly lower combined specific gravity for the Florida and Nevada aggregates and higher for the Alabama and California aggregates.
- Reflux: consistently higher combined specific gravity for all four aggregates.
- Ignition Oven: lower combined specific gravity for the Alabama and Florida aggregates and higher for the Nevada and California aggregates.

The consequences of using a specific extraction method on the properties of the blend aggregates are summarized in Table 7. The consequences are expressed in terms of the percent of time that the mix designer may over-estimate or underestimate a given property and how this may impact the acceptance of the mix.

Agg Pro-Pass 4.75 sieve

> Pass 0.07 siev

Con bulk spec grav

10.2

by to for a RAI studused combler the

met sour requesthat used RAI the

Table 7. Consequences of extraction method on mix design.

Aggregate Property	Centrifuge	Reflux	Ignition Oven
Passing 4.75 mm sieve	Close estimate 100% of time.	Close estimate 50% of time and 25% of time over- or underestimate. May result in spec violation 50% of time.	Close estimate 75% of time and 25% of time over-estimate. May results in spec violation 25% of time.
Passing 0.075 mm sieve	Close estimate 50% of time and 25% of time over- or underestimate. May result in spec violation 50% of time.	Close estimate 50% of time and 25% of time over- or underestimate. May result in spec violation 50% of time.	Over-estimate 50% of time and under-estimate 50% of time. May result in spec violation 50% of time.
Combined bulk specific gravity, dry	Over-estimate 50% of time and under-estimate 50% of time.	Over-estimate 100% of time.	Over-estimate 50% of time and under-estimate 50% of time.

10.2 Impact of RAP Specific Gravity on VMA

The final step of the analysis investigated the potential for error in VMA caused by the estimated RAP aggregate specific gravity (G_{sb}). The blend G_{sb} was calculated for different RAP contents using the RAP aggregate G_{sb} that was estimated for each RAP material using the traditionally used methods as were previously defined in this study as Methods A, B and C. The blend G_{sb} for different RAP contents was then used to calculate the VMA of the RAP-containing asphalt mixture which in turn was compared to the true VMA of the same mix. The true VMA was calculated from the blend G_{sb} for different RAP contents using the virgin aggregate specific gravities for the new and RAP aggregates in the mix.

Figures 11 to 13 summarize the impact of the errors associated with the different methods of determining $G_{\rm sb}$ for the RAP aggregate on VMA for all four aggregate sources when the centrifuge, reflux, and ignition oven were used to determine the required properties for the RAP aggregates, respectively. In practice, a VMA error that is within \pm 0.2% is considered acceptable. Therefore, this level of error was used to assess the appropriateness of the different methods of estimating $G_{\rm sb}$ for the RAP aggregate. Table 8 summarizes this analysis in terms of the percent of time that the mix designer may over-estimate or under-estimate the VMA and how this action would impact the final mix at the reported RAP contents.

Oven S SH

2

rse and coarse ver, the her fine sistently

nd fine oduced

specific

the fine

gravity

it is the

s of the

specific

ida and

Il four

na and

s of the

res.

rates.




Figure 11. Difference in VMA versus RAP content based on centrifuge (error bars represent minimum and maximum difference in VMA.)

Figur bars 1




Figure 12. Difference in VMA versus RAP content based on reflux (error bars represent minimum and maximum difference in VMA).




Figure 13. Difference in VMA versus RAP content based on ignition oven (error bars represent minimum and maximum difference in VMA).

(error bars

(error bars

Table 8. Impact of extraction method on VMA.

Extraction Method	RAP Content	Method A	Method B (0.75Pba)	Method B (1.00Pba)	Method B (1.25Pba)	Method C
	10%	Close estimate 100% of time.	Close estimate 100% of time.	Close estimate 100% of time.	Close estimate 100% of time.	Over-estimate 50% of time. The design will be un- conservative 50% of time
Centrifuge	30%	Close estimate 100% of time.	Over-estimate 25% of time. The design will be un- conservative 25% of time.	Close estimate 100% of time.	Under- estimate 100% of time.	Over-estimate 100% of time. The design will be un- conservative 100% of time
50%		Over-estimate 25% of time. The design will be un-conservative 25% of time.	Over-estimate 50% of time. The design will be un- conservative 50% of time.	Under- estimate 50% of time.	Under- estimate 100% of time.	Over-estimate 100% of time. The design will be un- conservative 100% of time
	10%	Close estimate 100% of time.	Close estimate 100% of time.	Close estimate 100% of time.	Close estimate 100% of time.	Over-estimate 50% of time. The design wil be un- conservative 50% of time
Reflux 309	30%	Over-estimate 25% of time. The design will be un-conservative 25% of time.	Over-estimate 50% of time. The design will be un- conservative 50% of time.	Close estimate 100% of time.	Under- estimate 100% of time.	Over-estimate 100% of time. The design wil be un- conservative 100% of time
	50%	Over-estimate 100% of time. The design will be un-conservative 100% of time.	Over-estimate 50% of time. The design will be un- conservative 50% of time.	Close estimate 100% of time.	Under- estimate 100% of time.	Over-estimate 100% of time. The design win be un- conservative 100% of time
	10%	Close estimate 100% of time.	Close estimate 100% of time.	Close estimate 100% of time.	Close estimate 100% of time.	Over-estimate 75% of time. The design will be un- conservative 50% of time
Ignition Oven	30%	Under-estimate 25% of time	Over-estimate 50% of time. The design will be un- conservative 50% of time.	Close estimate 100% of time.	Under- estimate 50% of time.	Over-estimate 100% of time. The design will be un- conservative 100% of time
	50%	Over- or under- estimate 25% of time. The design will be un- conservative 25% of time.	Over-estimate 75% of time. The design will be un- conservative 75% of time.	Close estimate 100% of time.	Under- estimate 100% of time.	Over-estimate 100% of time. The design wi- be un- conservative 100% of time

VMA error is within ±0.2%

Table 9 shows the overall assessment based on the data generated in this study from the four evaluated aggregates along with the maximum expected error in VMA. The data in Table 9 show the computed error in VMA calculation depending

on the RAP perce determine the R between 25 and 5 aggregate specific A) using the centr

Table

Methods for estimating RAJ aggregate specific gravity

Method A8

Method B h, i

s using measured sp aggregate along wi h assuming asphalt binder content for i i assumed asphalt c

11. OVERALL

This study evand ignition over laboratory simula (hard limestone) (rhyolite). The pwere compared tusing a specific ethe Superpave in the impact of the RAP aggregate simple RAP in a typic aggregates the fo

• The igr content were us factor i extracti

on the RAP percentage in the mix, the extraction technique and the method used to determine the RAP aggregate specific gravity. For example, for RAP content between 25 and 50%, the computed error in VMA was within +/- 0.4% if the RAP aggregate specific gravity was directly measured on extracted aggregate (i.e. Method A) using the centrifuge or the reflux.

Table 9. Overall summary of expected error in VMA for the evaluated aggregate sources.

Methods for estimating RAP		Expected					
aggregate]	Extraction Methods					
specific gravity	Centrifuge	Reflux	Ignition Oven	Error in VMA			
Method Ag	≤ 25%	≤ 25%	≤ 10%	± 0.2%			
1110410471	25% - 50%	25% - 50%	10% - 25%	± 0.4%			
Method B h. i	≤ 10%	≤ 10%	≤ 15%	± 0.2%			
	10% - 20%	10% - 20%	15% - 25%	± 0.4%			

^g using measured specific gravities of coarse and fine fractions of the extracted RAP aggregate along with the measured percent passing 4.75 mm sieve material in the RAP. assuming asphalt absorption along with measured theoretical maximum specific gravity and

binder content for RAP.

assumed asphalt absorption for the RAP aggregate within $\pm 25\%$ of the true value.

11. OVERALL CONCLUSIONS AND RECOMMENDATIONS

This study evaluated the impact of extraction methods (i.e. centrifuge, reflux, and ignition oven) on the extracted aggregate properties and binder content of laboratory simulated RAP mixtures with four different aggregate sources: Alabama (hard limestone), California (granodiorite), Florida (soft limestone), and Nevada (rhyolite). The properties of the various extracted aggregates from simulated RAP were compared to the respective virgin aggregate properties. The consequences of using a specific extraction method on the properties of the aggregates that are part of the Superpave mix design method were examined and summarized. Additionally, the impact of the errors associated with the different methods of determining the RAP aggregate specific gravity on VMA was evaluated for different percentages of RAP in a typical asphalt mixture. Based on the testing with a limited set of aggregates the following recommendations can be made:

The ignition method appears to give the most accurate results for asphalt content of RAP. Note that in this study, no aggregate correction factors were used for the ignition method results as development of the correction factor is not possible with most RAP sources in the field. The solvent extraction methods do not appear to remove all of the aged binder from the

0% of time. he design will e unonservative 0% of time ver-estimate

30% of time. he design will mservative 10% of time

ver-estimate 10% of time. ie design will unnservative 0% of time

'ст-estimate % of time. e design will uniservative

% of time er-estimate 1% of time. design will 411-

servative % of time :r-estimate % of time. design will

ervative % of time -estimate

of time. design will ervative

of time -estimate of time. lesign will

wative. of time estimate of time.

esign will rative of time

stud y Tor in ending

RAP, and consequently RAP asphalt contents using these methods tend to be lower than they actually are.

- One of the most important properties that must be determined for the RAP is the specific gravity of the RAP aggregate. The RAP aggregate Gsb is critical to an accurate determination of VMA, which is one of the key mix properties used in mix design and quality assurance. For high RAP content mix designs, the best method for determining the RAP aggregate specific gravities is to use a solvent extraction method (centrifuge or reflux) to recover the aggregate and then test the coarse and fine parts of the recovered aggregate using AASHTO T 85 and T 84, respectively. The ignition furnace may also be used to recover the RAP aggregate except for some aggregate types which undergo significant changes in specific gravity when subjected to the extreme temperatures used in the ignition method. In this study, the soft Florida limestone was an example of this problem. Note that all of the methods used to recover the RAP aggregate are likely to cause seemingly small errors in the G_{sh} results. As RAP contents approach 50%, the net effect may be an error in the VMA determination of \pm 0.4%. This magnitude of uncertainty is one of the reasons why it may be appropriate to perform additional performance related tests on high RAP mix designs to assure resistance to rutting, moisture damage, fatigue cracking, and low temperature cracking.
- Another method for estimating the RAP aggregate specific gravity is the approach recommended in NCHRP Report 452. This method was evaluated in this study as Method B and involves determining the maximum theoretical specific gravity (G_{mm}) of the RAP material using AASHTO T 209. From the G_{mm} and the asphalt content of the RAP, the effective specific gravity (G_{se}) of the RAP aggregate can be determined. Although some agencies use the G_{se} for the RAP aggregate in the calculation of VMA, the authors strongly advise against this practice. Other agencies try to correct the G_{se} to an estimated G_{sb} using an assumed value for asphalt absorption. This correction is only reliable when the asphalt absorption can be assumed with confidence. The correction is very sensitive to the assumed asphalt absorption value and can lead to errors in VMA that are 0.5% or more.

12. ACKNOWLEDGMENTS

The authors would like to thank the Federal Highway Administration for its intellectual and financial support of this study. The efforts of the Florida Department of Transportation in locating and supplying an aggregate source are also appreciated. The efforts of the Granite Construction in supplying the Nevada and California aggregate sources are also appreciated.

13. REFERE

American Assi Specificati Edition, 20

Asphalt Institt Asphalt In

Hajj E.Y., Lor Extraction Report WI

Lynn T., Jame Volumetrie No. 1998, 2007.

McDaniel R.S. the Super Transporta

Prowell B.D. Properties Research (

Shultz R.L., Laboratory

14. DISCUSS

DR. HONGB quality control extraction me check the diffinished mixidifferent for a difference was

DR. ELIE HA you are asking in the lab, so v

DR. XIE: Yo you check the

ods tend to

or the RAP gate Gsb is ne key mix AP content ite specific reflux) to irts of the ively. The except for ific gravity method. In olem. Note e likely to s approach f +/- 0.4%. it may be high RAP te, fatigue

vity is the evaluated maximum ASHTO T: effective Although ulation of gencies try or asphalt rption can ve to the A that are

on for its epartment preciated. California

13. REFERENCES

- American Association of State Highway and Transportation Officials (AASHTO), Standard Specifications for Transportation Materials and Methods of Sampling and Testing, 29th Edition, 2009.
- Asphalt Institute, Superpave Mix Design, Superpave Series No. 2 (SP-2), Third Edition, Asphalt Institute, 2001.
- Hajj E.Y., Loria L., Morian N., Kvasnak A., Nelson J., Sebaaly P.E., West R., "Effect of Extraction Methods on the Properties of Aggregates in Reclaimed Asphalt Pavements," Report WRSC-Rep-10-02, FHWA Report, Forthcoming.
- Lynn T., James R.S., Wu P.S., and Jared D.M., "Effect on Aggregate Degradation on Volumetric Properties of Georgia's Hot-Mix Asphalt," *Transportation Research Record*, No. 1998, Transportation Research Board of the National Academies, Washington, D.C. 2007.
- McDaniel R.S., and Anderson R.M., Recommended Use of Reclaimed Asphalt Pavement in the Superpave Mix Design Method: Technician's Manual, NCHRP Report 452, Transportation Research Board, Washington, D.C., 2001.
- Prowell B.D. and Carter C.B., "Interim Report: Evaluation of the Effect on Aggregate Properties of Samples Extracted Using the Ignition Furnace," Virginia Transportation Research Council, 2000.
- Shultz R.L., "Asphalt Extraction Study," Washington State Transportation Materials Laboratory, 1998.

14. DISCUSSION

DR. HONGBIN XIE: Good morning. I have two questions. The first one is the quality control for the mixing part. I noticed the AC Contents by three different extraction methods were all lower comparing to your true asphalt content. Did you check the difference between your batching weight and the mix weight after you finished mixing? I also wondered why AC content results were that significantly different for all three methods. Did you do any quality control to see if any of the difference was caused by the missing asphalt maybe in the mixing procedure?

DR. ELIE HAJJ: I'm not sure if I got your question correctly. So if I may rephrase, you are asking whether we checked the weights when we made the simulated RAP in the lab, so we had a certain batch weight for the aggregate and for the binder....

DR. XIE: You had mixing, aging and a lot of handling, right? My question is, "Did you check the batching weight or your target weight when you batched everything

up together to the final mixed weight?" You need to see if anything significant is missing.

DR. HAJJ: I don't know exactly if we checked the numbers, but what I know we were consistent in the production of the mixtures. All mixtures had the same amount of aggregate material at starting. Now usually, and I can talk about our lab practice, when we conduct mix designs or when we prepare samples for performance testing, we monitor the weight that goes into the mold and if we notice a large difference from the expected weight, then something went wrong during handling of the material. Maybe the batch weight was not correct. But I don't know if we specifically checked the weights before and after. Maybe Nathan Morian has some input on that matter. Nathan, do you want to answer the question? Nathan was heavily involved in the preparation and testing of the samples.

MR. NATHAN MORIAN: We actually didn't check the weights, but we were very, very careful in scraping the bowls, scraping the pans, especially during the twice a day stirring. That's quite a bit of handling of each mixture, but we didn't specifically check the before and after weights, but we scraped the pans as best as physically possible. I guess that's the best we can do.

DR. HAJJ: I hope that answers your question.

DR. XIE: Yes, because I'm doing this routinely so I know exactly what might happen if you have a lot of handling, and that can actually affect your results significantly. Then the other question is, "When you do the specific gravity on your recovered aggregates either from the chemical extraction or from the ignition oven test, did you run the specific gravity on the entire sample?" Basically, the gradation as you show on your paper has changed from their initial gradation. I assume you didn't do any adjustment on the gradation, you just ran the entire sample after extraction?

DR. HAJJ: No adjustments were made. That was the purpose of the study, not to do any adjustments to the results and assess the impact of those techniques. So for example once you end up with a mix, we extracted the RAP aggregate, sieved it on No. 4 and then ran AASHTO T 85 on the plus No. 4 material.

DR. XIE: What I'm trying to get to is that the specific gravity test, particularly the fine aggregate specific gravity, can be affected by the gradation. If you have ignition oven extraction in particular, you're introducing additional minus No. 200 material, and that can affect the results.

DR. HAJJ: Correct, and that's the purpose of the study. The whole purpose of the study was to quantify that effect on the specific gravities and other material properties and what influence will have on the mix design parameters such as the VMA. You're right on target. We know the different extraction techniques are going to affect your gradation to a certain extent and they're going to have some influence,

but how sig comfortable calculations

DR. XIE: (

DR. HAJJ:

MR. JOHN understand you're runni are you acc into the mix aggregate, v because it's

DR. HAJJ: absorption?

MR. VICTO

DR. HAJJ: referred to a of the actual So if we go is going to larger. I tot: number as a That was the deviation, becomes sig showing tha gravity measurements to really go influence the

MR. VICTC

DR. HAJJ:

DR. GERM question tha the mechani smaller amo on these typ

but how significant is that influence and to what level of RAP content I will be comfortable using the measurements without jeopardizing the volumetric calculations.

DR. XIE: Okay, thanks.

DR. HAJJ: Thank you.

MR. JOHN VICTORY: Thanks. I have one question. I'm trying to see if I understand all that I know about this. You're taking the extracted aggregate and you're running a G_{sb} on that and using that calculation to calculate the VMA. How are you accounting for the absorption that takes place? When you put that number into the mix design, you are assuming a certain amount of absorption for the RAP aggregate, when in the real world, the RAP aggregate has very little absorption because it's already accounted for. How are you accounting for that difference here?

DR. HAJJ: Actually, that's the thing. But do you know in the real world what is that absorption?

MR. VICTORY: We don't know what the number is but it should be very low.

DR. HAJJ: That's the key. So since we don't know, when we went with what's referred to as Method B in the study, the assumption was to use the same absorption of the actual RAP aggregate and then deviate from that value by plus or minus 25%. So if we go to a lower value or even still a lower assumed absorption, then the VMA is going to deviate more from your target VMA and the difference is going to be larger. I totally agree that you don't know what it is and we had to use a certain number as a benchmark and then deviate from that number to assess the impact. That was the purpose of the deviations. I can tell that we checked not only for 25% deviation, but we looked into even larger deviations. Really the difference in VMA becomes significant. So when it comes to the high RAP, more than 25%, the study is showing that you need to extract and recover your aggregates and run your specific gravity measurements and gradation. That seems to be the best approach if you want to really get good characterization of the RAP material and not significantly influence the VMA calculation.

MR. VICTORY: Okay, thanks.

DR. HAJJ: Thanks.

DR. GERMAN CLAROS: Really nice presentation and good work. I think the real question that we need to have here is how much these changes in VMA will affect the mechanical properties of that material? Because maybe we're dealing with a smaller amount that it will not make any difference, and I think the basic principle on these types of mixes is to know what are the mechanical properties of the mix

ficant is

now we amount bractice, testing, fference of the if we as some an was

re very, twice a sifically ysically

might results in your n oven idation ne you e after

t to do So for d it on

rly the mition sterial,

of the aterial as the going sence,

that we want to specify to have a good performance since at the end of the day that is what is important.

DR. HAJJ: Very good question, but at the same time, there is a specification at the end that needs to be met. For a state DOT, even if you still have good mechanical properties, but if you fail the project job mix formula for VMA, your mix is considered an out of spec mix. So I totally agree that mechanical properties are important and affect your pavement performance but we still have specifications that are based on mixture volumetrics. There was a study that was conducted at UNR by Peter Sebaaly and Gabriel Bazi where they looked at the impact of what they called construction variability, and I think that VMA was one of the parameters that they looked at to see its impact on the mixture mechanical properties such as rutting resistance, stiffness, and others. It was conducted about six or seven years ago, and I don't recall any more the conclusion of the study. But you're totally right, at the end how much difference is allowable without jeopardizing the mixture properties.

Succ Bala Requ

Fujie 7 Tom S

*Texas : College f-zhou@ t-scullio

** Texa Austin, ' Robert.i

ABSTRAC the perfc many ag are cons within i optimum findings in OAC improve. (HWTT) with inc RAP/RA study. I RAP mi cr.ackin_{ Addition compaci potentia selected that the mix as 1 through interest. at least

The ora